



U CORES



Part No.	unit	A	B	C1	C2(norm)	D(min)	E(min)
SU4110	mm	40.6	11.2	9.5	8.38	23.88	2.79
	in	1.6 ± 0.020	$.440 \pm 0.020$	$.375 \pm 0.015$	0.33	0.94	0.1
SU4111	mm	40.6	11.2	12.1	8.38	23.88	2.79
	in	1.6 ± 0.020	$.440 \pm 0.0100$	$.475 \pm 0.015$	0.33	0.94	0.1
SU5527	mm	54.9	27.6	16.3	10.5	33.9	17
	in	2.16 ± 0.0	1.085 ± 0.020	$.643 \pm 0.012$	0.42	1.3	0.65
SU5529	mm	54.9	27.6	23.2	10.5	33.9	17
	in	2.16 ± 0.025	1.085 ± 0.020	$.912 \pm 0.015$	0.42	1.3	0.65
SU6527	mm	65.1	32.5	27	10	44.2	22.2
	in	2.565 ± 0.053	1.28 ± 0.012	1.063 ± 0.016	0.394	1.741	0.874
SU6533	mm	65.1	32.5	20	12.5	40.1	20
	in	2.565 ± 0.053	1.28 ± 0.012	$.788 \pm 0.016$	0.493	1.545	0.764
SU8020	mm	80	38.1	19.8	9.9	59.3	28.1
	in	3.15 ± 0.035	1.5 ± 0.025	$.780 \pm 0.015$	0.39	2.334	1.108

Part No.	AL value(nH/ N²), Tolerance: $\pm 12\%$				Path Length	Cross Section	Volume
	26 μ	40 μ	60 μ	90 μ	le(mm)	Ae(mm²)	Ve(mm³)
SU4110	-	56	77.5	109	8.52	0.80	6.81
SU4111	-	72	95	138	8.52	1.01	8.60
SU5527	67	-	-	-	16.80	1.72	28.90
SU5529	85	-	-	-	16.80	2.44	40.99
SU6527	89	-	-	-	21.90	2.70	59.10
SU6533	82	-	-	-	19.90	2.50	49.75
SU8020	64	-	-	-	27.30	1.95	53.20